

L6 ANSWER 19 OF 24 CA COPYRIGHT 2006 ACS on STN
 AN 122:87744 CA
 ED Entered STN: 18 Feb 1995
 TI Admixtures for cement, and cement compositions
 containing the admixtures
 IN Kyogoku, Yasuhiro; Kanamori, Shinji; Ida, Makio; Mihara, Toshio
 PA Denki Kagaku Kogyo Kk, Japan
 SO Jpn. Kokai Tokkyo Koho, 5 pp.
 CODEN: JKXXAF

DT Patent

LA Japanese

IC ICM C04B022-12

ICS C04B022-14; C04B024-26; C04B028-02; C04B028-22

CC 58-1 (Cement, Concrete, and Related Building Materials)

FAN. CNT 1

PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
JP 06256053	A2	19940913	JP 1993-39922	19930301
PRAI JP 1993-39922		19930301		

CLASS

PATENT NO.	CLASS	PATENT FAMILY CLASSIFICATION CODES
JP 06256053	ICM	C04B022-12
	ICS	C04B022-14; C04B024-26; C04B028-02; C04B028-22
	IPCI	C04B0022-12 [ICM,5]; C04B0022-14 [ICS,5]; C04B0024-26 [ICS,5]; C04B0028-02 [ICS,5]; C04B0028-22 [ICS,5]

AB Th admixts. contain latent hydraulic binders, Ca fluoroaluminates, inorg. sulfates, thickeners, and water reducing agents, and are mixed with cement to give the cement compns. Concrete prepared from a composition containing portland cement 56, fly ash 24, Ca fluoroaluminate 10, and II-type anhydrite 10 weight parts 460, water 158.1, fine aggregate 889, coarse aggregate 741, and Darex Super 100PHX (water reducing agent) 6.9 kg/m3, with addition of Me cellulose 20, and air-entraining agent 23 g/m3, had excellent workability and 3-, 7-, and 28-day compressive strength 260, 340, and 480 kg/cm2, resp.

ST calcium fluoroaluminate sulfate cement; fly ash calcium fluoroaluminate concrete

IT Concrete

- Cement
- fly ash
- water
- water reducing agent